

Characterization of carbon nanotube containing polymer membranes

T.Koschine, K. Rätzke, F.Faupel CAU Kiel, Technische Fakultät, Institut für Materialwissenschaft, Lehrstuhl für Materialverbunde, Kaiserstraße 2, 24143 Kiel, GERMANY

M.M. Khan, T. Emmeler, V. Filiz, V. Abetz, Helmholtz-Zentrum Geesthacht, Zentrum für Material- und Küstenforschung GmbH, Institut für Polymerforschung, Max-Planck-Straße 1, 21502 Geesthacht, GERMANY

C | A | U

Christian-Albrechts-Universität zu Kiel

Faculty of Engineering


Institute for Material Science, Chair for Multicomponent Materials

Motivation - membranes

Separation of gas mixtures

High permeability **P** = high solubility **S** * high diffusivity **D**

with $D \propto \exp\left[-\frac{v^*}{v_f}\right]$



Selectivity for two components A and B: $\alpha_{AB} = \frac{P_A}{P_B}$

Why polymers?

- Changes in **free volume** affects diffusivity directly without changes in solubility
- Structural modifications
- Ease of preparation and handling

Motivation – This Work

Why PIM-1?


- High permeability
 - High free volume
- ⇒ promising membrane material

Why mixed matrix membranes / MWCNTs?

- Mechanical performance of material increased – effect on long term stability?
 - Increasing membrane and mechanical properties of an known and very good membrane material.
- This Work**
- Aging (storage at room temperature) leads to reduction in free volume*
 - Here usage, i.e. how does free volume change comparing freshly prepared and used membranes.
 - How is the effect of CNT on aging / usage ?

*Stephan Harms et al, JOURNAL OF ADHESION, 88(7), 608-619, 2012

Physical aging




- Decrease of **P** over time / while usage
- Reason: Reduced free volume holes?

Why PALS?


- PALS can detect microscopic free volume

$$D \propto \exp\left[-\frac{v^*}{v_f}\right]$$

Positron Annihilation Lifetime Spectroscopy (PALS)




Positron annihilation in porous materials



Typical PALS spectrum

Tao-Eldrup Model: $\tau_3 \leftrightarrow$ average hole size

- radioactive decay → positron
- positron + electron → ortho-positronium (o-Ps)
- trapping in voids
- decay by interaction with electrons from wall



- average **free volume void sizes** determine average ortho-positronium **lifetime**
- ortho-positronium **intensity** depends on concentration of holes, spur electrons and positron acceptors

Hole radius $r \uparrow \Rightarrow$ overlap wavefunction, $\Delta R \downarrow \Rightarrow$ decay probability $\downarrow \Rightarrow$ lifetime $\tau_3 \uparrow$
Ortho-positronium **intensity** = hole **concentration** \times o-Ps **formation probability**

S. J. Tao, J. Chem. Phys. 56, (1972) 5499, M. Eldrup et al., J. Chem. Phys. 63, (1981) 51

PLEPS

PLEPS at FRMII

Pulsed Low Energy Positron System

Positron energy:
 $E_{kin} = 0.2 \text{ keV} - 22 \text{ keV}$

sample holder:
 $T = 80 \text{ K} - 500 \text{ K}$


W. Egger, L. Ravelli

University of armed forces Munich, Neubiberg and FRM II Munich


Werner Egger et al, phys. stat. sol.c, 4(10), 3969-3972 2007

Sample preparation

Polymerization PIM-1




Functionalization of MWCNTs




- Upto 2wt.%, f-MWCNTs dispersed in PIM-1 matrix.
- Thin (700 nm) PIM-1 and PIM-1 f-MWCNT MMM prepared on PAN support layer
- Used (~300 days for gas separation) and as-cast samples prepared for PALS measurements.

Muntazim M Khan et al, JOURNAL OF MEMBRANE SCIENCE, 436, 109-120, 2013

Permeation Measurements



- O₂ permeance higher with f-MWCNTs
- Degradation over time
- Agglomeration with more than 2 wt.% ⇒ Performance decrease




- Relative reduction of permeance slower with higher f-MWCNT content
- Better long term stability


Gas measurement condition:
Temperature = 27°C
feed pressure = 2 bar.

Muntazim M Khan et al, NANOSCALE RESEARCH LETTERS, 7, 504, 2012

PALS Measurements



- Lower o-Ps lifetime and intensity at the surface
- Diffusion of free volume to surface.*
- Strong **reduction** of free volume holes after usage.
- Free volume holes maybe less connected



- Less reduction of free volume** with MWCNTs
- Larger holes** when f-MWCNTs incorporated.
- Lifetime measurement results in expected regime for physical aging.

Open symbols: POSWIN evaluation

Solid symbols: LT evaluation

*Stephan Harms et al, JOURNAL OF ADHESION, 88(7), 608-619, 2012

Conclusion

- Better Permeation** with added f-MWCNTs in PIM-1 matrix.
- Better mechanical stability
- Less free volume reduction** during usage with f-MWCNTs
- CO₂/N₂ separation performance above Robeson 2008 upper bound

Promising mixed matrix membrane material

Acknowledgements

- EU-Project HARCANA for financial support for membrane preparation
- BMBF project POSIMETHOD for financial support of PALS measurements.

Contact

Tönjes Koschine
Institute for Materials Science, Chair for Multicomponent Materials
Faculty of engineering - CAU Kiel
E-mail: tk@tf.uni-kiel.de
Tel.: +49 (0)431 880 6234